

InsulPatch®


Datasheet

Laminates for PV Electrical Insulating Applications

MATERIAL COMPOSITION

TEST:	RESULTS:
Thickness*	281 µm
Width Range	51 - 1700 mm
Weight	285 g/m ²
Density	1.15 g/cm ³
EVA Colors	All

EVA / PET / EVA



TECHNICAL CHARACTERISTICS

TEST:	TEST SPECIFICATION(S):	RESULTS:
Tensile Strength at Break (MD/TD)	Internal Testing - Data Available	40 MPa (MD) / 50 MPa (TD)
Elongation at Break (MD/TD)	Internal Testing - Data Available	145% (MD) / 80% (TD)
EVA Peel Strength from Encapsulant	Internal Testing - Data Available	≥ 40 N/cm
Relative Thermal Index (RTI)	Suitable for continuous use at 85°C	105

ELECTRICAL INSULATION TESTING PERFORMANCE

TEST:	TEST SPECIFICATION(S):	RESULTS:
Partial Discharge	IEC 60664-1	≥ 1000 VDC
Dielectric Strength	UL 746 A	≥ 17 kV
Volume Resistivity		16 10 ¹⁰ ohm-cm
Comparative Tracking Index (CTI)	Thickness tested: 3.0mm	≥ 600V

*Theoretical nominal

This product is covered by one or more U.S. patents and pending U.S. and other patent applications.
Typical Data - Not Specification



Tomark-Worthen
64 Watkin Ave
Chadds Ford, PA 19317
USA

Phone: 1-610-978-1889
Email: info@tomark-worthen.com
www.tomark-worthen.com

TOMARK  **WORTHEN**