

# PhotoMark® eTPU™ Datasheet

High Performance Aliphatic Polyether Thermoplastic Polyurethane Film

## OVERVIEW

PhotoMark eTPU is a high performance aliphatic polyether thermoplastic polyurethane film intended for processing by lamination into a range of glass/plastics components. Available in thicknesses from 50µm to 250µm.



## TECHNICAL CHARACTERISTICS

Excellent laminated transparency	Medium durometer
Excellent hydrolysis resistance	Contains adhesion promoter
Excellent microbial resistance	Medium modulus
Good low temperature flexibility	Excellent cold impact

## TESTING PERFORMANCE

TEST:	TEST SPECIFICATION(S):	RESULTS:
Tensile Strength	ASTM D638	45 MPa
Modulus	ASTM D638	2.7 MPa (100%, 300%)
Elongation	ASTM D638	500 %
Tear Resistance	ASTM D624	37 N/mm
Hardness	ASTM D2240	80 Shore A
Specific Gravity	ASTM D792	1.07
Softening Point (TMA)	ASTM D3418	80 °C
Melting Point (TMA)	ASTM D3418	140 °C
Light Transmittance	ASTM D1746	90 %
Haze	ASTM D1003	0.31 %
Refractive Index	ASTM D542	1.5

\*Theoretical nominal

This product is covered by one or more U.S. patents and pending U.S. and other patent applications.  
Typical Data - Not Specification



Tomark-Worthen  
64 Watkin Ave  
Chadds Ford, PA 19317  
USA

Phone: 1-610-978-1889  
Email: info@tomark-worthen.com  
www.tomark-worthen.com

**TOMARK**  **WORTHEN**